

Material type: Y-PSZ

DEGUSSIT FZY

Properties		Unit	Specific value
Main components		-	ZrO ₂ , Y ₂ O ₃ , Al ₂ O ₃
Purity		wt.-%	> 99.7
Density		g / cm ³	≥ 5.5
Open Porosity		vol.-%	0
Average Size of Crystallites		µm	30
Bending Strength σ_m	DIN EN 843-1	MPa	400
Compressive Strength		MPa	2000
Young's Modulus	static	GPa	200
Hardness	Knoop, 100 g	GPa	17
Maximum Service Temperature in Air		°C	1700
Linear Coefficient of Expansion	20 - 100 °C	10 ⁻⁶ / K	9.2
	20 - 500 °C	10 ⁻⁶ / K	10.4
	20 - 1000 °C	10 ⁻⁶ / K	10.9
Specific Heat	20 °C	J / (kg * K)	400
Thermal conductivity	100 °C	W / (m * K)	2.5
Resistivity	20 °C	Ω * cm	10 ¹⁰
	600 °C	Ω * cm	4 * 10 ²
	1000 °C	Ω * cm	15
Typical Colour		-	white

The data indicated on this table are in line with the introductory German Industrial Standard DIN 40680 and relate to test specimens from which they were obtained. They are not unconditionally applicable to other forms of the same material. The data must be regarded as indicative only. All data refer to a temperature of 20 °C, unless otherwise specified.

The material is extremely resistant to corrosion.